

## LUMIRROR® X30

Lumirror® X30 is a pigmented filled black polyester film with an excellent stability and good pigment distribution.

Properties	Unit	#38 (150G)	#50 (200G)	#75 (300G)	#100 (400G)	#125 (500G)	#188 (750G)	#
Thickness	MMV Mic	38	50	75	100	125	250	
Tensile Strength	MD Mpa	225	225	215	215	205	196	
	TD MPa	225	225	215	215	176	166	
Elongation at Break	MD %	125	125	120	120	120	150	
	TD %	125	125	120	120	120	130	
Thermal Shrinkage at 150DegCx30min	MD %	1.4	1.4	1.3	1.3	1.2	1	
	TD %	0.2	0.2	0.4	0.2	0.2	0.8	
Optical Density	-	>0.5	>1.5	>2.5	>3	>4	>4	

### PSG Group Ltd. - Disclaimer

All technical information and related data supplied by or on behalf of PSG Group Ltd. (and subsidiary companies) is believed to be accurate and complete. However, it will remain the responsibility of the purchaser / user to determine the suitability of each product for a particular application and shall assume all risk and liability in connection therewith.

No warranty is implied with regard to information or recommendations given by our distributors and or subcontractors. The descriptions of products and services displayed on this web site and the terms under which they are given may be modified at any time without notice. In any event or occurrence, our liability is strictly limited to the value of the original invoice. Any links on this site are for the convenience of the visitor only and we are not responsible for their content.

Lumirror® registered trademark of Toray Plastics Europe. Only Toray Plastics Europe makes Lumirror® brand polyester film



Plastic Shims & Gaskets Ltd  
 49-53 Glengall Road  
 London  
 SE15 6NF  
 United Kingdom  
 Phone- +44 (0) 20 7740 9705  
 Fax- +44 (0) 20 7277 5654  
 e-mail- sales@psgroup.co.uk